

What is claimed is:

sub A, >

1. An antimicrobial copolymer obtainable by copolymerizing (component I) aliphatically unsaturated monomers which have been functionalized by means of an ester group and at least singly functionalized by means of a tertiary amino group with (component II) another aliphatically unsaturated monomer which has been at least singly functionalized by means of an amino group, where component I and component II are different from one another.
2. The antimicrobial copolymer as claimed in claim 1, wherein component II is composed of aliphatically unsaturated monomers which have been at least singly functionalized by means of a tertiary amino group.
3. The antimicrobial copolymer as claimed in claim 1 or 2, wherein component I is composed of aliphatically unsaturated monomers whose ester group has been at least singly functionalized by means of an amino group.
4. The antimicrobial copolymer as claimed in one of claims 1 to 3, wherein component I is composed of acrylate or methacrylates which have been at least singly functionalized by means of a tertiary amino group.
5. The antimicrobial polymer as claimed in one of claims 1 to 4, wherein each of components I and II is an aliphatically unsaturated monomer functionalized by means of a tertiary amino group and having the general formula



where R^1 : is a branched, unbranched or cyclic, saturated or

"Amended page"

unsaturated hydrocarbon radical having up to 50 carbon atoms which may have substitution by O atoms, N atoms or S atoms, and

R^2 and R^3 are branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radicals having up to 25 carbon atoms, which may have substitution by O atoms, N atoms or S atoms, where R^2 and R^3 are identical or different,

with the proviso that R^1 in monomers of component I contains an ester group.

6. The antimicrobial coating made from antimicrobial copolymers as claimed in one of claims 1 to 5, wherein the copolymerization is carried out on a substrate.

7. The antimicrobial coating made from antimicrobial copolymers as claimed in one of claims 1 to 5, wherein the copolymerization is carried out as a graft polymerization of a substrate.

8. The antimicrobial coating as claimed in claim 7, wherein the substrate is activated prior to the graft polymerization by UV radiation, plasma treatment, corona treatment, flame treatment, ozonization, electrical discharge or γ -radiation.

9. The antimicrobial coating as claimed in claim 7, wherein the substrate is activated prior to the graft polymerization by UV radiation with a photoinitiator.

10. A process for preparing antimicrobial copolymers by copolymerizing (component I) aliphatically unsaturated monomers which have been functionalized by means

0926479.012502

sub A₁

25

sub A₂³⁰

of an ester group and a tertiary amino group with (component II) another aliphatically unsaturated monomer which has been at least singly functionalized by means of an amino group, where components I and II are different from one another.

11. The process as claimed in claim 10, wherein component II is composed of aliphatically unsaturated monomers which have been at least singly functionalized by means of a tertiary amino group.

12. The process as claimed in claim 10 or 11, wherein component I is composed of aliphatically unsaturated monomers whose ester group has been at least singly functionalized by means of an amino group.

13. The process as claimed in one of claims 10 to 12, wherein component I is composed of acrylate or methacrylates which have been at least singly functionalized by means of a tertiary amino group.

14. The process as claimed in one of claims 10 to 13, wherein each of components I and II is an aliphatically unsaturated monomer functionalized by means of a tertiary amino group and having the general formula



where R^1 : is a branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radical having up to 50 carbon atoms which may have substitution by O atoms, N atoms or S atoms, and

R^2 and R^3 : are branched, unbranched or cyclic, saturated or unsaturated hydrocarbon radicals having up to 25 carbon atoms, which

09926479.0125002

15
A
cont

may have substitution by O atoms, N atoms or S atoms, where
 R^2 and R^3 are identical or different,
with the proviso that R^1 in monomers of component I contains an ester group.

5 15. The process as claimed in one of claims 10 to 14,
wherein
the copolymerization is carried out on a substrate.

10 16. The process as claimed in one of claims 10 to 15,
wherein
the copolymerization is carried out as a graft polymerization of a substrate.

15 17. The process as claimed in claim 16,
wherein
the substrate is activated prior to the graft polymerization by UV radiation, plasma
treatment, Corona treatment, flame treatment, ozonization, electrical discharge
or γ -radiation.

EXPH₂

20 18. The process as claimed in claim 17,
wherein
the substrate is activated prior to the graft polymerization by UV radiation with a
photoinitiator.

25 19. The use of the antimicrobial copolymers as claimed in one of claims 1 to 9 for
producing products with an antimicrobial coating comprising the copolymer.

20. The use of the antimicrobial polymers as claimed in one of claims 1 to 9 for
producing items in medical technology with an antimicrobial coating comprising
the copolymer.

30

21. The use of the antimicrobial copolymers as claimed in one of claims 1 to 9 for
producing hygiene items with an antimicrobial coating comprising the copolymer.

0926479-013502

"Amended page"

22. The use of the antimicrobial copolymers as claimed in one of claims 1 to 9 in surface coatings, protective paints or in other coatings.

ADD A_3 >

0926479.012502